

WO00045734

Publication Title:

WO00045734

Abstract:

Abstract not available for WO00045734 Data supplied from the esp@cenet database - Worldwide

Courtesy of <http://v3.espacenet.com>

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | |
|--|-----------|---|
| (51) International Patent Classification ⁷ : A61F 2/00, A61K 9/14 | A1 | (11) International Publication Number: WO 00/45734 (43) International Publication Date: 10 August 2000 (10.08.00) |
| (21) International Application Number: PCT/US00/01425 (22) International Filing Date: 20 January 2000 (20.01.00) (30) Priority Data: 09/241,703 2 February 1999 (02.02.99) US (71) Applicant: WRIGHT MEDICAL TECHNOLOGY, INC. [US/US]; 5677 Airline Road, Arlington, TN 38002 (US). (72) Inventors: HAGGARD, Warren, Oliver; 6600 Stephan Ridge Drive, Bartlett, TN 38135 (US). KAUFMAN, Michael, Earl; 2818 Morning Woods Drive, Cordova, TN 38018 (US). PARR, Jack, Eldon; 3568 Davieshire Cove, Memphis, TN 38133 (US). (74) Agent: NABINGER, Robert, C.; Fish & Richardson P.C., 225 Franklin Street, Boston, MA 02110-2804 (US). | | (81) Designated States: AU, CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> |
| (54) Title: CONTROLLED RELEASE COMPOSITE (57) Abstract A composite is disclosed having a controlled rate of dissolution. The composite includes (a) a first region that includes a first composition that includes calcium sulfate, the first region exhibiting a first rate of dissolution; and (b) a second region that includes a second composition that includes calcium sulfate, the second region exhibiting a second rate of dissolution, the first rate of dissolution being different from the second rate of dissolution. | | |

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | | | |
|----|--------------------------|----|--|----|--|----|--------------------------|
| AL | Albania | ES | Spain | LS | Lesotho | SI | Slovenia |
| AM | Armenia | FI | Finland | LT | Lithuania | SK | Slovakia |
| AT | Austria | FR | France | LU | Luxembourg | SN | Senegal |
| AU | Australia | GA | Gabon | LV | Latvia | SZ | Swaziland |
| AZ | Azerbaijan | GB | United Kingdom | MC | Monaco | TD | Chad |
| BA | Bosnia and Herzegovina | GE | Georgia | MD | Republic of Moldova | TG | Togo |
| BB | Barbados | GH | Ghana | MG | Madagascar | TJ | Tajikistan |
| BE | Belgium | GN | Guinea | MK | The former Yugoslav Republic of Macedonia | TM | Turkmenistan |
| BF | Burkina Faso | GR | Greece | ML | Mali | TR | Turkey |
| BG | Bulgaria | HU | Hungary | MN | Mongolia | TT | Trinidad and Tobago |
| BJ | Benin | IE | Ireland | MR | Mauritania | UA | Ukraine |
| BR | Brazil | IL | Israel | MW | Malawi | UG | Uganda |
| BY | Belarus | IS | Iceland | MX | Mexico | US | United States of America |
| CA | Canada | IT | Italy | NE | Niger | UZ | Uzbekistan |
| CF | Central African Republic | JP | Japan | NL | Netherlands | VN | Viet Nam |
| CG | Congo | KE | Kenya | NO | Norway | YU | Yugoslavia |
| CH | Switzerland | KG | Kyrgyzstan | NZ | New Zealand | ZW | Zimbabwe |
| CI | Côte d'Ivoire | KP | Democratic People's Republic of Korea | PL | Poland | | |
| CM | Cameroon | KR | Republic of Korea | PT | Portugal | | |
| CN | China | KZ | Kazakstan | RO | Romania | | |
| CU | Cuba | LC | Saint Lucia | RU | Russian Federation | | |
| CZ | Czech Republic | LI | Liechtenstein | SD | Sudan | | |
| DE | Germany | LK | Sri Lanka | SE | Sweden | | |
| DK | Denmark | LR | Liberia | SG | Singapore | | |
| EE | Estonia | | | | | | |

5

CONTROLLED RELEASE COMPOSITE

Background of the Invention

The invention relates to controllably dissolving a composite.

10 Controlled release of medication *in vivo* is the subject of much research. Various methods and release agents have been suggested, tested and marketed. Calcium sulfate has been utilized as filler for bone cavities as it is capable of being spontaneously adsorbed and replaced by bone. Calcium sulfate, formed from the hemihydrate, has been used as a controlled release agent alone for the filling of bone
15 cavities and in combination with additives such as medicaments and pesticides. As a carrier for medicaments, it has been useful *in vivo* because it is biocompatible and is progressively resorbed by the body, thereby eliminating the need for secondary surgical procedures.

One application for a calcium sulfate controlled release agent is the local
20 delivery of medicaments *in vivo*. The ideal characteristics of a local medicament delivery system are (1) biodegradability, (2) biocompatibility, (3) prolonged pharmaceutical release (e.g., over a period of at least 4 to 6 weeks), (4) reproducibility, (5) predictable pharmacokinetics, and (6) controllability.

One of the disadvantages to the use of calcium sulfate as a carrier is that,
25 for some medicaments, the medicament is eluted from the calcium sulfate matrix at too rapid of a rate.

Summary of the Invention

In general, the invention features a composite having a controlled rate of dissolution. The composite includes at least two regions, each of which includes a
30 composition that includes calcium sulfate. A first region of the composite exhibits a rate of dissolution that is different from a second region of the composite. These composites are useful for filling bone voids and for delivering calcium and medicaments *in vivo* for sustained periods of time. In one embodiment, the regions

5 are in the form of layers. In another embodiment, the first region surrounds the second region.

The preferred calcium sulfate is selected from the group consisting of alpha-calcium sulfate hemihydrate, beta-calcium sulfate hemihydrate, calcium sulfate dihydrate prepared from alpha-calcium sulfate hemihydrate, calcium sulfate
10 dihydrate prepared from beta-calcium sulfate hemihydrate, and combinations thereof.

In one embodiment, the first composition further includes a medicament, preferably a medicament selected from the group consisting of tetracycline hydrochloride, vancomycin, tobramycin, gentamicin, cephalosporin, cis-platinum,
15 ifosfamide, methotrexate, doxorubicin hydrochloride, transforming growth factor beta, bone morphogenic protein, demineralized bone matrix ("DBM"), basic fibroblast growth factor, platelet-derived growth factor, polypeptide growth factors, lidocaine hydrochloride, bupivacaine hydrochloride, ketorolac tromethamine, or a combination thereof. In another embodiment, the second composition also includes
20 a medicament.

In one embodiment, the first composition includes calcium sulfate dihydrate prepared from alpha-calcium sulfate hemihydrate, and preferably, the second composition includes calcium sulfate dihydrate prepared from beta-calcium sulfate hemihydrate.

25 Preferred compositions are prepared by contacting with an aqueous liquid an alpha-calcium sulfate hemihydrate having a mean particle size of from about 12 μm to about 23.5 μm . In one embodiment, at least 80% of the alpha-calcium sulfate hemihydrate has a particle size of from about 12 μm to about 22 μm , more preferably from about 16 μm to about 22 μm . In preferred composites, from
30 about 0.1% to about 2.0% of the alpha-calcium sulfate hemihydrate has a particle size of less than about 2 μm . In one embodiment, the alpha-calcium sulfate hemihydrate has a density of from about 2.6 to about 2.9 g/cm^3 . In other embodiments, the alpha-calcium sulfate hemihydrate has a purity greater than 98

5 wt.% calcium sulfate hemihydrate. The preferred range for the BET surface area of the alpha-calcium sulfate hemihydrate is from about 0.2 m²/g to about 1.0 m²/g.

Preferably the calcium sulfate is prepared from alpha-calcium sulfate hemihydrate having a purity greater than 98 weight % ("wt. %") calcium sulfate hemihydrate, a BET surface area in the range of from about 0.35 m²/g to about 0.9
10 m²/g, a density in the range of from about 2.73 to about 2.80 g/cm³, and a mean particle size of about 16 μm to about 22 μm. Preferably from about 90 to about 95 wt. % of the alpha-calcium sulfate hemihydrate has a particle size distribution from about 1 μm to about 45 μm.

In one embodiment, the first composition is prepared by contacting with
15 an aqueous liquid calcium sulfate consisting essentially of beta-calcium sulfate hemihydrate having a mean particle size in the range of from about 10 μm to about 15 μm. In other embodiments, the beta-calcium sulfate hemihydrate has a purity greater than 98 wt.% calcium sulfate hemihydrate. The beta-calcium hemihydrate can also have a BET surface area of from about 4.5 m²/g to about 7.5 m²/g, more
20 preferably from about 5 m²/g to about 6 m²/g, and a density of from about 2.5 g/cm³ to about 2.6 g/cm³. In another embodiment, the first composition is prepared by contacting with an aqueous liquid calcium sulfate consisting essentially of beta-calcium sulfate hemihydrate having a purity greater than 98 wt.% calcium sulfate hemihydrate, a BET surface area in the range of from about 4.5 m²/g to about 7.5
25 m²/g, a density in the range of from about 2.5 g/cm³ to about 2.6 g/cm³, and a mean particle size in the range of from about 13 μm to about 14 μm.

In another aspect, the invention features a method of delivering medicament *in vivo*. The method includes implanting the above-described composite into a mammal.

30 The composite of the invention permits the controlled dissolution of regions that include a calcium sulfate composition, as well as the controlled release of additives such as, e.g., medicaments and pesticides.

Other features and advantages of the invention will be apparent from the following description of the preferred embodiments thereof, and from the claims.

5

Description of the Preferred Embodiments

The composite includes two regions that exhibit different rates of dissolution with respect to each other. The regions of the composite are macroscopic and can exist in a variety of forms in the composite such as, e.g., layers and geometrical shapes, e.g., spheres. The regions can be continuous or
10 discontinuous, and one or more regions can exist within another region or regions.

The regions consist of compositions that include calcium sulfate and, optionally, an additive. Examples of sources of calcium sulfate suitable for use in preparing the compositions include alpha-calcium sulfate hemihydrate powder, beta-calcium sulfate hemihydrate powder, calcium sulfate dihydrate powder made
15 from calcium sulfate hemihydrate powders including alpha-calcium sulfate hemihydrate and beta-calcium sulfate hemihydrate, and combinations thereof.

A preferred alpha-calcium sulfate hemihydrate powder has a purity greater than 98 wt.% calcium sulfate hemihydrate, a BET surface area of from about 0.2 m²/g to about 1.0 m²/g (preferably from about 0.35 m²/g to about 0.9 m²/g, more
20 preferably from about 0.35 m²/g to about 0.7 m²/g), a density of about 2.6 g/cm³ to about 2.9 g/cm³ (more preferably from about 2.73 g/cm³ to about 2.80 g/cm³), and a mean particle size of from about 12 μm to about 23.5 μm. Preferably from about 0.1% to about 2.0% of the alpha-calcium sulfate hemihydrate has a particle size of less than about 2.0 μm. Preferably at least 80% of the alpha-calcium sulfate
25 hemihydrate has a particle size of from about 12 μm to about 22 μm, more preferably from about 16 μm to about 22 μm.

A preferred beta-calcium sulfate hemihydrate powder has a purity greater than 98 wt.% calcium sulfate hemihydrate, a BET surface area of from about 4.5 m²/g to about 7.5 m²/g (more preferably from about 5 m²/g to about 6 m²/g), a
30 density of from about 2.5 g/cm³ to about 2.6 g/cm³, and a mean particle size of from about 10 μm to about 15 μm (more preferably from about 13 μm to about 14 μm).

The calcium sulfate composition of each region, the combination of regions, and the composite can be selected to achieve a desired rate of elution of one or more additives present in the composite, a desired rate of dissolution of the pellet

- 5 including its regions, and combinations thereof. The composite can include regions of calcium sulfate prepared from a single form of calcium sulfate (e.g., alpha-calcium sulfate hemihydrate or beta-calcium sulfate hemihydrate powder), or multiple forms of calcium sulfate (e.g., a combination of one or more of alpha-calcium sulfate hemihydrate, beta-calcium sulfate hemihydrate, and the dihydrate
10 prepared from alpha-calcium sulfate hemihydrate and beta-calcium sulfate hemihydrate). One example of a useful composite includes an interior region of calcium sulfate dihydrate prepared from beta-calcium sulfate hemihydrate, and an exterior region surrounding the interior region where the exterior region includes calcium sulfate dihydrate prepared from alpha-calcium sulfate hemihydrate.
15 Another example of a useful composite includes an interior region that includes calcium sulfate dihydrate prepared from alpha-calcium sulfate hemihydrate, and an exterior region surrounding the interior region where the exterior region includes calcium sulfate dihydrate made from beta-calcium sulfate hemihydrate. Other examples of composites include one or more calcium sulfate dihydrate regions
20 prepared from a combination of alpha and beta-calcium sulfate hemihydrate.

One example of a useful calcium sulfate composition that includes a mixture of beta-calcium sulfate hemihydrate powder and alpha-calcium sulfate hemihydrate powder, includes a weight ratio of beta-calcium sulfate hemihydrate powder to alpha-calcium sulfate hemihydrate powder of between 0 and about 3.
25 Narrower ranges of this ratio, e.g., 0 to about 0.11, 0 to about 0.05, and 0 to about 0.02, are also contemplated. When used to carry growth factors, the weight ratio of the beta-calcium sulfate hemihydrate powder to the alpha-calcium sulfate hemihydrate powder may range up to about 3:1.

The composition, a region of the composite, or the composite, itself, can
30 also include additives that are controllably released as the region dissolves. Examples of suitable additives include medicaments and pesticides. Examples of useful medicaments include antibiotics, chemotherapeutic agents, growth factors, and analgesics. Examples of useful antibiotics include tetracycline hydrochloride, vancomycin, cephalosporins, and aminoglycosides such as tobramycin and

- 5 gentamicin. Examples of chemotherapeutic agents include cis-platinum, ifosfamide, methotrexate, and doxorubicin hydrochloride (Adriamycin®). Examples of growth factors include transforming growth factor beta (TGF-Beta), bone morphogenic protein ("BMP"), demineralized bone matrix ("DBM"), basic fibroblast growth factor, platelet-derived growth factor, and other polypeptide
- 10 growth factors. Examples of analgesics include anesthetics such as lidocaine hydrochloride (Xylocaine®), bipivacaine hydrochloride (Marcaine®), and non-steroidal anti-inflammatory drugs such as ketorolac tromethamine (Toradol®).

The composite can include distinct regions each containing 0 to about 25 wt. % additive, preferably about 2 wt. % to about 10 wt. % additive, most preferably

15 about 2 wt. % to about 5 wt. % additive.

One method of preparing a composite includes preparing two or more regions, and then combining, e.g., through pressure, adhesion or molding, two or more regions to form the composite, e.g., a pellet, a tablet or other geometric shape. The regions can be prepared by combining a source of calcium sulfate with an

20 aqueous liquid to form a calcium sulfate composition, and then molding or applying pressure to the calcium sulfate composition to form the region.

The aqueous liquid can include salt, e.g., sodium chloride, i.e., it may be a saline solution. An alpha- or beta-calcium sulfate hemihydrate powder will convert to the dihydrate form upon contact with water or saline. The water to

25 calcium sulfate weight ratio is preferably in the range of from about 0.22 to about 1, more preferably in the range of from about 0.27 to about 0.35 for alpha-calcium sulfate hemihydrate, and from about 0.65 to about 0.85 for beta-calcium sulfate hemihydrate powder. The consistency of a calcium sulfate powder (i.e., ml solution/grams calcium sulfate) is proportional to its surface area and is dependent

30 upon the morphology of the crystal.

Additives can be incorporated into the composite using a variety of methods including, e.g., incorporating the additive into the calcium sulfate powder mixture (e.g., by mixing the additive with the calcium sulfate in powdered form prior to forming the calcium sulfate and aqueous liquid composition), addition of

5 the additive to the calcium sulfate and aqueous liquid composition, and
impregnating the formed region with an additive, e.g., by contacting the region with
an additive in the form of a liquid or aerosol. Another useful method for
incorporating an additive into the composite includes dissolving or suspending the
additive into a solution and subsequently impregnating the additive into the calcium
10 sulfate powder.

The composite can be formulated to provide a predetermined rate of
dissolution or rate of release. Factors that influence the rate of dissolution or rate of
release of the composite include, e.g., the composition of the composite, the
composition of the regions, and the structure of the composite, e.g., the location of
15 the regions within the composite. In addition, the form of calcium sulfate, the
number of different forms of calcium sulfate, and the amount of each form of
calcium sulfate present in the composition can be selected to provide a region
having a desired rate of dissolution.

The composite, or a region of the composite, can be pre-formed for ease
20 of use or custom formulated to meet a specific rate of dissolution, or rate of release
or profile, e.g., a release rate or profile specified by a surgeon during the
performance of an operation.

The invention will now be further described by way of the following
examples.

25

5

EXAMPLES

Dissolution Test Procedure

The dissolution rate of a pellet was determined by immersing the pellet in distilled water and periodically taking it out of the solution so that the pellet could be weighed. 100 ml of distilled water was placed in a polyethylene bottle. A pellet
10 was immersed in the distilled water and the bottle was then placed in a water bath maintained at 37°C.

At 24 hour intervals (+/- 1 hour) the pellet was removed from the bottle, weighed ("wet weight"), dried in an oven at 40°C for 40 minutes, and weighed again ("dry weight"). The weight was recorded to the nearest milligram.

15 The polyethylene bottle was then refilled with 100 ml of fresh distilled water and the dried pellet was immersed in the distilled water. The bottles were again placed in the water bath maintained at a temperature of 37°C.

The above process was repeated for 8 days or until the pellet had completely dissolved. The average weight % ("wt. %") pellet remaining at each
20 interval for each of the pellets tested was determined.

Elution Test Procedure

The elution rate of the medicament from a pellet was determined by weighing a pellet and then placing the pellet in a water-tight plastic container
25 containing 20 ml of phosphate buffered saline (Dulbeccos Phosphate Buffered Saline, Sigma Chemical Co.). The container was then immersed in a water bath maintained at 37°C for 24 hours. After 24 hours, a 2-4 ml sample of the eluant was removed and pipeted into a labeled cryogenic vial, which was then used to determine the concentration of tobramycin present in the sample as described
30 below.

A metal mesh captured the pellet as the remaining solution was discarded. The container was then filled with 20 ml of fresh phosphate buffered saline solution, and the pellet was again immersed in the saline solution for another 24 hour period. After 24 hours a 2-4 ml sample was removed from the container

5 and tested to determine the concentration of tobramycin present in the sample, as described below. This process was repeated for a total of seven days.

The concentration of tobramycin present in the 2-4 ml samples was measured using a TDX FLx automated fluorescence polarization analyzer (Abbott Laboratories). To obtain a reading, the sample was diluted to a concentration in the
10 range of between 1-10 ug/ml and analyzed by TDX to determine the concentration, in ug/ml, of tobramycin in the sample. Dilutions varied from 1000 to 1x, from day 1 to day 7, respectively. The average tobramycin concentration, in ug/ml, of the pellets tested was determined for each interval.

15 Sample Preparation

Example 1 – Dual β T/ α T Pellets

Pellets containing an outer layer prepared from beta-calcium sulfate hemihydrate and tobramycin and an inner core prepared from alpha-calcium sulfate hemihydrate and tobramycin ("dual β T/ α T pellets") were prepared as follows. 5 g
20 beta-calcium sulfate hemihydrate (U.S. Gypsum) and 0.09 g stearic acid (J.T. Baker) were combined and mixed on a roll mixer for approximately 10 minutes. 0.29 g tobramycin sulfate (Eli Lilly) dissolved in 3.75 g water was combined with 5.09 g of the beta-calcium sulfate/stearic acid mixture. The composition was allowed to hydrate for 1 minute and then mixed for one minute to form a paste.

25 The resulting paste was cast into a bottomless mold. A 3 mm Osteoset T pellet prepared from alpha-calcium sulfate hemihydrate and 4 % tobramycin sulfate (Eli Lilly) was inserted into the paste in the mold cavity. The paste was smoothed around the pellet to completely cover the pellet to form a dual β T/ α T pellet. The dual β T/ α T pellet was covered and allowed to dry for 15 minutes at ambient
30 temperature, and then turned over and allowed to dry for 2 minutes at ambient temperature. The dual β T/ α T pellet was covered and dried for approximately 2 hours. The dual β T/ α T pellet was then removed from the mold, placed in an oven and dried for approximately 5 hours at 40°C.

- 5 Dual β T/ α T pellets made by this process yielded, on average, 4 % by weight tobramycin sulfate (approximately 3.2 mg/composite).

Example 2 – Dual α T/ β T Pellets

- Pellets containing an outer layer prepared from alpha-calcium sulfate hemihydrate and tobramycin and an inner core prepared from beta-calcium sulfate hemihydrate and tobramycin ("dual α T/ β T pellets") were prepared as follows. 20 g
10 alpha-calcium sulfate hemihydrate (USG) was combined with 0.38 g stearic acid and mixed on a roll mixer for approximately 10 minutes. 1.14 g tobramycin sulfate dissolved in 5 g water was combined with 20.38 g of the alpha-calcium
15 sulfate/stearic acid mixture. The composition was allowed to hydrate for 1 minute and then mixed for one minute to form a paste ("the alpha paste"). The resulting alpha paste was then cast into a bottomless 4.8 mm diameter mold.

- A 3 mm calcium sulfate and tobramycin pellet prepared from beta-calcium sulfate hemihydrate ("the 3mm beta pellet") was prepared as follows. 10 g
20 beta-calcium sulfate hemihydrate and 0.18 g stearic acid were combined and mixed on a roll mixer for approximately 10 minutes. 0.58 g tobramycin sulfate dissolved in 7.5 g water was combined with 10.18 g of the calcium sulfate/stearic acid mixture. The composition was allowed to hydrate for 1 minute and then mixed for one
25 minute to form a paste. The resulting paste was cast into a 3 mm diameter bottomless mold and dried to form a 3 mm beta pellet.

- The dried 3 mm beta pellet was then inserted into the 4.8 mm mold cavity that had been filled with the above-described alpha paste. The alpha paste was smoothed over the surface of the beta pellet so as to encase the beta pellet and form a dual α T/ β T pellet. The dual α T/ β T pellet was cast at ambient temperature,
30 turned over after 7 minutes, and allowed to dry for 5 minutes at ambient temperature. The dual α T/ β T pellet was then covered and dried for approximately 2 hours. The dual α T/ β T pellet was then removed from the mold, placed in an oven and dried for approximately 5 hours at 40°C.

5 Dual α T/ β T pellets made by this process yielded 4 % by weight tobramycin sulfate (approximately 4 mg/composite).

10 Example 3 – Dual α T/ α T Pellets

Pellets containing an outer layer prepared from alpha-calcium sulfate hemihydrate and tobramycin and an inner core prepared from alpha-calcium sulfate hemihydrate and tobramycin ("dual α T/ α T pellets") were prepared and follows. 25 g alpha-calcium sulfate hemihydrate was combined with 0.475 g stearic acid and
15 mixed on a roll mixer for approximately 10 minutes. 1.43 g tobramycin sulfate dissolved in 6.25 g water was combined with 24.475 g of the alpha-calcium sulfate/stearic acid mixture. The composition was allowed to hydrate for 1 minute and then mixed for one minute to form a paste. The resulting paste was cast into a bottomless mold.

20 A 3 mm Osteoset T pellet prepared from alpha-calcium sulfate hemihydrate and containing 4 % tobramycin sulfate (Eli Lilly) was inserted into an empty mold and covered over with the above-described paste to form a dual α T/ α T pellet. The dual α T/ α T pellet was cast at ambient temperature, turned over after 10 minutes, and allowed to dry for 4 minutes at ambient temperature. The dual α T/ α T
25 pellet was covered and dried for approximately 48 hours. The dual α T/ α T was then removed from the mold, placed in an oven and dried for approximately 8.5 hours at 40°C.

Dual α T/ α T pellets made by this process yielded 4 % by weight tobramycin sulfate (approximately 4.6 mg/composite).

30 Five pellets prepared according to each of Examples 1-3 were tested according to the Dissolution Test Procedure set forth above. The average wt. % of pellet remaining at each interval for Examples 1-3 is recorded in Table 1. Three pellets prepared according to each of Examples 1-3 were tested according to the

- 5 Elution Test Procedure set forth above. The average tobramycin concentration in ug/ml of three pellets of each of Examples 1-3 is recorded in Table 2.

TABLE 1

| Example | Day 0 Ave. % residual | Day 1 Ave. % residual | Day 2 Ave. % residual | Day 3 Ave. % residual | Day 4 Ave. % residual | Day 5 Ave. % residual | Day 6 Ave. % residual | Day 7 Ave. % residual | Day 8 Ave. % residual |
|-----------------------------------|-----------------------------|--------------------------------|-----------------------------|-----------------------------|-----------------------------|-----------------------------|-----------------------------|-----------------------------|-----------------------------|
| 1. Dual β T/ α T | 100 | 62.4 | 38.8 | 22.2 | 10.0 | 3.0 | 0.0 | | |
| 2. Dual α T/ β T | 100 | 67.8 | 39.1 | 23.6 | 9.1 | 1.6 | 0.0 | | |
| 3. Dual α T/ α T | 100 | 71.3 | 50.4 | 33.0 | 19.6 | 9.8 | 3.8 | 0.5 | 0.0 |

10

5

TABLE 2

| Example | Ave Initial wt of Composite (mg) | Ave Initial wt of tobramycin (mg) | Day 1 Ave. Concentration (ug/ml) | Day 2 Ave. Concentration (ug/ml) | Day 3 Ave. Concentration (ug/ml) | Day 5 Ave. Concentration (ug/ml) | Day 7 Ave. Concentration (ug/ml) | Day 10 Ave. Concentration (ug/ml) | Day 15 Ave. Concentration (ug/ml) | Day 22 Ave. Concentration (ug/ml) |
|--------------------------------|----------------------------------|-----------------------------------|----------------------------------|----------------------------------|----------------------------------|----------------------------------|----------------------------------|-----------------------------------|-----------------------------------|-----------------------------------|
| 1. Dual β T/ α T | 639.0 | 17.12 | 750 | 60.9 | 16.2 | 6.4 | 3.5 | 3.3 | 3.5 | 5.0 |
| 2. Dual α T/ β T | 813.7 | 21.81 | 820 | 78.8 | 9.7 | 5.5 | 3.1 | | | |
| 3. Dual α T/ α T | 956.3 | 25.41 | 1277 | 130.5 | 41.1 | 17.3 | 6.6 | 5.0 | 0.0 | |

10 Other embodiments are within the following claims. For example, although the composite has been described as having two regions, the composite can include multiple regions of different calcium sulfate compositions such that within one composite there exists multiple regions having differing dissolution rates. In addition, each region can include one or more additives.

15 What is claimed is:

5

1. A composite having a controlled rate of dissolution, said composite comprising:

(a) a first region comprising a first composition that comprises calcium sulfate, said first region exhibiting a first rate of dissolution; and

10 (b) a second region comprising a second composition that comprises calcium sulfate, said second region exhibiting a second rate of dissolution, said first rate of dissolution being different from said second rate of dissolution.

15 2. The composite of claim 1, wherein said calcium sulfate of said first composition is selected from the group consisting of alpha-calcium sulfate hemihydrate, beta-calcium sulfate hemihydrate, calcium sulfate dihydrate, or a combination thereof.

20 3. The composite of claim 2, wherein said calcium sulfate of said second composition is selected from the group consisting of alpha-calcium sulfate hemihydrate, beta-calcium sulfate hemihydrate, calcium sulfate dihydrate, or a combination thereof.

25 4. The composite of claim 1, wherein said regions are in the form of layers.

5. The composite of claim 1, wherein said first region surrounds said second region.

30

6. The composite of claim 1, wherein said first composition further comprises a medicament.

- 5 7. The composite of claim 6, wherein said second composition further comprises a medicament.
8. The composite of claim 6, wherein the medicament is selected from the group consisting of tetracycline hydrochloride, vancomycin, tobramycin,
10 gentamicin, cephalosporin, cis-platinum, ifosfamide, methotrexate, doxorubicin hydrochloride, transforming growth factor beta, bone morphogenic protein, demineralized bone matrix, basic fibroblast growth factor, platelet-derived growth factor, polypeptide growth factors, lidocaine hydrochloride, bipivacaine hydrochloride, ketorolac tromethamine, or a combination thereof.
- 15 9. The composite of claim 7, wherein the medicament is selected from the group consisting of tetracycline hydrochloride, vancomycin, tobramycin, gentamicin, cephalosporin, cis-platinum, ifosfamide, methotrexate, doxorubicin hydrochloride, transforming growth factor beta, bone morphogenic protein,
20 demineralized bone matrix, basic fibroblast growth factor, platelet-derived growth factor, polypeptide growth factors, lidocaine hydrochloride, bipivacaine hydrochloride, ketorolac tromethamine, or a combination thereof.
10. The composite of claim 1, wherein said first composition
25 comprises calcium sulfate dihydrate prepared from alpha-calcium sulfate hemihydrate.
11. The composite of claim 10, wherein said first composition further comprises a medicament.
- 30 12. The composite of claim 11, wherein said second composition comprises calcium sulfate dihydrate prepared from beta-calcium sulfate dihydrate.

- 5 13. The composite of claim 12, wherein said second composition further comprises a medicament.
14. The composite of claim 1, wherein said first composition comprises calcium sulfate dihydrate prepared from alpha-calcium sulfate
10 hemihydrate and said second composition comprises calcium sulfate dihydrate prepared from beta-calcium sulfate hemihydrate.
15. The composite of claim 1, wherein said first composition is prepared by contacting with an aqueous liquid an alpha-calcium sulfate hemihydrate
15 having a mean particle size of from about 12 μm to about 23.5 μm .
16. The composite of claim 15, wherein at least 80% of said alpha-calcium sulfate hemihydrate has a particle size of from about 12 μm to about 22 μm .
- 20 17. The composite of claim 15, wherein at least 80% of said alpha-calcium sulfate hemihydrate has a particle size of from about 16 μm to about 22 μm .
18. The composite of claim 15, wherein from about 0.1% to about 2.0% of said alpha-calcium sulfate hemihydrate has a particle size of less than about
25 2 μm .
19. The composite of claim 15, wherein said alpha-calcium sulfate hemihydrate has a purity greater than 98 wt.% calcium sulfate hemihydrate.
- 30 20. The composite of claim 15, wherein said alpha-calcium sulfate hemihydrate has a BET surface area of from about 0.2 m^2/g to about 1.0 m^2/g .
21. The composite of claim 15, wherein said alpha-calcium sulfate hemihydrate has a density of from about 2.6 g/cm^3 to about 2.9 g/cm^3 .

5

22. The composite of claim 15, wherein said composite further comprises medicament.

23. The composite of claim 15, wherein said calcium sulfate consists
10 essentially of alpha-calcium sulfate hemihydrate having a purity greater than 98 wt.% calcium sulfate hemihydrate, a BET surface area in the range of from about 0.35 m²/g to about 0.9 m²/g, a density in the range of from about 2.73 to about 2.80 g/cm³, and a mean particle size of from about 16 μm to about 22 μm.

15 24. The composite of claim 15, wherein from about 90 to about 95 wt.% of the alpha-calcium sulfate hemihydrate has a particle size distribution from about 1 μm to about 45 μm.

25 25. The composite of claim 1, wherein said first composition is prepared by contacting with an aqueous liquid calcium sulfate consisting essentially of beta-calcium sulfate hemihydrate having a mean particle size in the range of from about 10 μm to about 15 μm.

26. The composite of claim 25, wherein said beta-calcium sulfate
25 hemihydrate has a purity greater than 98 wt.% calcium sulfate hemihydrate.

27. The composite of claim 25, wherein said beta-calcium sulfate hemihydrate has a BET surface area of from about 5 m²/g to about 6 m²/g.

30 28. The composite of claim 25, wherein said beta-calcium sulfate hemihydrate has a density of from about 2.5 g/cm³ to about 2.6 g/cm³.

29. The composite of claim 25, wherein said composite further comprises medicament.

5

30. The composite of claim 25, wherein said beta-calcium sulfate hemihydrate has a BET surface area of from about 4.5 m²/g to about 7.5 m²/g.

31. The composite of claim 25, wherein said calcium sulfate consists
10 essentially of beta-calcium sulfate hemihydrate having a purity greater than 98 wt.% calcium sulfate hemihydrate, a BET surface area in the range of from about 4.5 m²/g to about 7.5 m²/g, a density in the range of from about 2.5 to about 2.6 g/cm³, and a mean particle size of about 13 μm to about 14 μm.

15 32. A method of delivering medicament *in vivo* comprising implanting a composite in a mammal, said composite comprising
(a) a first region comprising a first composition that comprises calcium sulfate, said first region exhibiting a first rate of dissolution,
(b) a second region comprising a second composition that comprises
20 calcium sulfate, said second region exhibiting a second rate of dissolution,
said first rate of dissolution being different from said second rate of dissolution, and
(c) a medicament.

25

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/01425

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61P 2/00; A61K 9/14

US CL : 424/472, 423, 489, 484; 514/951

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/472, 423, 489, 484
514/951

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

BRS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-----------|--|-----------------------|
| X ---- | US 5,614,206A (RANDOLPH et al) 25 March 1997, see entire document | 1-3, 5-32 ---- |
| Y | | 4 |
| X | US 5,807,567A (RANDOLPH et al) 15 September 1998, see entire document | 1-32 |

☐ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

| | | |
|---|-----|--|
| * Special categories of cited documents: | *T* | later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention |
| *A* document defining the general state of the art which is not considered to be of particular relevance | *X* | document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone |
| *B* earlier document published on or after the international filing date | *Y* | document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art |
| *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) | *A* | document member of the same patent family |
| *O* document referring to an oral disclosure, use, exhibition or other means | | |
| *P* document published prior to the international filing date but later than the priority date claimed | | |

Date of the actual completion of the international search

08 MARCH 2000

Date of mailing of the international search report

81 MAR 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

TODD D WARE

Telephone No. (703) 308-1235